



The mark of responsible forestry

Paged Colour

Paged Colour is a high quality finish birch plywood made with waterproof resin and designed for both structural and non-structural applications. It is characterised by high durability and strength, while its surface provide a decorative and easy to maintain surface.

KEY BENEFITS AND APPLICATIONS

- Main application areas include: fit-out (commercial and marine), interior cladding, furniture making and joinery, shelving, fittings for kitchens, retail space and playgrounds
- High durability and strength
- Hygienic and easy to maintain
- High UV resistance
- Made in Poland

STANDARD SIZES** [mm]

1250x2500 1500x2500/3000*

- *With white or grey coating
- **Other formats available on request

DIMENSIONAL DEVIATION AS PER EN 315 & EN 324

Length / width	Deviation
< 1000 mm	± 1 mm
1000 – 2000 mm	± 2 mm
> 2000 mm	± 3 mm

STRAIGHTNESS AND SQUARENESS DEVIATION AS PER EN 315 & EN 324

	Deviation
Straightness	± 0,1% or ± 1mm/m
Squareness	± 0,1% or ± 1mm/m

COATING - Melamine film

Colour	Thickness (g/m²)	RAL	
White	90/205, 140/340	9010	
Red	60/172 3020		
Blue	60/172	5005	
Yellow	90/200	1021	
Green	60/164	6028/6029	

NOMINAL THICKNESS WITH STANDARD DEVIATION, NUMBER OF PLIES, DENSITY AS PER EN 315, EN 323 & EN 324

Nominal Thickness (mm)*	Number of plies (pcs)		Deviation m)	Weight (kg/m²)	Density avg. (kg/m³)
9	7	-0,7	+0,5	6,3	_
12	9	-0,8	+0,6	8,4	
15	11	-0,9	+0,7	10,5	640-760**
18	13	-0,9	+0,7	12,6	
21	15	-1,0	+0,8	14,7	
24	17	-1,1	+0,9	16,8	
27	19	-1,8	+1,4	18,9	
30	21	-1,9	+1,5	21	

^{*}Other thicknesses available upon request

RELEASE OF FORMALDEHYDE (EN 717-1) BONDING QUALITY (EN 314-2) Class 3 Class 3 Edge machining, CNC machining and drilling on request 1. General Terms of Sales available from www.sklejkapaged.pl 2. Declaration of Performance available from www.sklejkapaged.pl 3. Film-faced plywood in-house norms and standards available from www.sklejkapaged.pl

^{**}As measured at 8-12% moisture content



