

Paged Form Plus

(softwood panel covered on both sides with special craft-based paper and phenolic film)



Znak odpowiedzialnej gospodarki leśnej

<p>Paged Form Plus is softwood plywood double overlaid: with kraft paper and phenolic film. The construction offers an upgrade in terms of resistance to water and durability and thereby increases the number of uses at least to 10. The overlay allows its user to achieve a spotless surface press. The thicknesses of softwood veneers are: 3,2 mm and 2,5 mm.</p>	<p>KEY BENEFITS AND APPLICATIONS</p> <ul style="list-style-type: none"> Main application areas include: formwork, pre-fabricated concrete elements, paving slabs and stones, transportation and packaging Rigidity and moisture resistance Ease of machining Multiple usage 	<p>STANDARD SIZES* 2500x1250; 2440x1220</p> <p>*Other formats available on request</p> <hr/> <p>DIMENSIONAL DEVIATION AS PER EN 315 & EN 324</p> <table border="1"> <thead> <tr> <th>Length/Width</th> <th>Deviation</th> </tr> </thead> <tbody> <tr> <td>< 1000 mm</td> <td>± 1 mm</td> </tr> <tr> <td>1000 – 2000 mm</td> <td>± 2 mm</td> </tr> <tr> <td>> 2000 mm</td> <td>± 3 mm</td> </tr> </tbody> </table> <hr/> <p>STRAIGHTNESS AND SQUARENESS DEVIATION AS PER EN 315 & EN 324</p> <table border="1"> <thead> <tr> <th></th> <th>Deviation</th> </tr> </thead> <tbody> <tr> <td>Straightness</td> <td>± 0,1% or ± 1mm/m</td> </tr> <tr> <td>Squareness</td> <td>± 0,1% or ± 1mm/m</td> </tr> </tbody> </table>	Length/Width	Deviation	< 1000 mm	± 1 mm	1000 – 2000 mm	± 2 mm	> 2000 mm	± 3 mm		Deviation	Straightness	± 0,1% or ± 1mm/m	Squareness	± 0,1% or ± 1mm/m																		
Length/Width	Deviation																																	
< 1000 mm	± 1 mm																																	
1000 – 2000 mm	± 2 mm																																	
> 2000 mm	± 3 mm																																	
	Deviation																																	
Straightness	± 0,1% or ± 1mm/m																																	
Squareness	± 0,1% or ± 1mm/m																																	
<p>NOMINAL THICKNESS WITH STANDARD DEVIATION, NUMBER OF PLYS, DENSITY AS PER EN 315, EN 323 & EN 324</p> <table border="1"> <thead> <tr> <th>Nominal Thickness (mm)*</th> <th>Number of plies (pcs)</th> <th>Standard Deviation min. (mm)</th> <th>Standard Deviation max. (mm)</th> <th>Weight (kg/m²)</th> <th>Density avg. (kg/m³)</th> </tr> </thead> <tbody> <tr> <td>15</td> <td>5</td> <td>-0,8</td> <td>0,7</td> <td>8,8</td> <td rowspan="5">585**</td> </tr> <tr> <td>18</td> <td>7</td> <td>-1,0</td> <td>0,7</td> <td>10,5</td> </tr> <tr> <td>21</td> <td>8</td> <td>-1,0</td> <td>0,8</td> <td>12,3</td> </tr> <tr> <td>24</td> <td>9</td> <td>-1,1</td> <td>0,9</td> <td>14,0</td> </tr> <tr> <td>27</td> <td>10</td> <td>-1,7</td> <td>1,4</td> <td>15,8</td> </tr> </tbody> </table> <p>*Other thicknesses available upon request **As measured at 8-12% moisture content</p>			Nominal Thickness (mm)*	Number of plies (pcs)	Standard Deviation min. (mm)	Standard Deviation max. (mm)	Weight (kg/m ²)	Density avg. (kg/m ³)	15	5	-0,8	0,7	8,8	585**	18	7	-1,0	0,7	10,5	21	8	-1,0	0,8	12,3	24	9	-1,1	0,9	14,0	27	10	-1,7	1,4	15,8
Nominal Thickness (mm)*	Number of plies (pcs)	Standard Deviation min. (mm)	Standard Deviation max. (mm)	Weight (kg/m ²)	Density avg. (kg/m ³)																													
15	5	-0,8	0,7	8,8	585**																													
18	7	-1,0	0,7	10,5																														
21	8	-1,0	0,8	12,3																														
24	9	-1,1	0,9	14,0																														
27	10	-1,7	1,4	15,8																														
<p>RELEASE OF FORMALDEHYDE (EN 717-1)</p> <p>E1 The product also meets the limit ½ E1</p>	<p>BONDING QUALITY (EN 314-2)</p> <p>Class 3</p>	<p>MACHINING</p> <p>Edge machining, CNC machining and drilling on request</p>																																
<p>COATING</p> <table border="1"> <tbody> <tr> <td>Film type – inner layer</td> <td>Kraft paper impregnated with phenolic resin</td> </tr> <tr> <td>Thickness</td> <td>390 g/m²</td> </tr> <tr> <td>Film type – outer layer</td> <td>Phenolic</td> </tr> <tr> <td>Thickness</td> <td>167 g/m²</td> </tr> <tr> <td>Colour</td> <td>Dark brown</td> </tr> </tbody> </table> <p>ADDITIONAL INFORMATION</p> <p>1. General Terms of Sales available from</p>			Film type – inner layer	Kraft paper impregnated with phenolic resin	Thickness	390 g/m ²	Film type – outer layer	Phenolic	Thickness	167 g/m ²	Colour	Dark brown																						
Film type – inner layer	Kraft paper impregnated with phenolic resin																																	
Thickness	390 g/m ²																																	
Film type – outer layer	Phenolic																																	
Thickness	167 g/m ²																																	
Colour	Dark brown																																	

			<p>www.sklejkapaged.pl. 2. Declaration of Performance available from www.sklejkapaged.pl. 3. Film-faced plywood in-house norms and standards available from www.sklejkapaged.pl.</p>
--	--	--	---

