

Paged ParquetPly

(hardwood birch or softwood pine plywood)



The mark of responsible forestry

Improved quality hardwood or softwood plywood for engineered flooring producers. Manufactured by Paged to strict thickness tolerance under controlled production regime that guarantees stable moisture and dimensional stability. Easy to machine and overlay with natural veneers.

KEY BENEFITS AND APPLICATION

- Main application areas include: parquet and engineered floors, stairs, interior design.
- Tight thickness tolerance
- Optimal moisture level of 5-9%
- High durability
- Dimensional stability
- Made in Poland from sustainably sourced wood

STANDARD SIZES [mm]*

Hardwood
1220x2440
1250x2500
2440x1220
2500x1250

Softwood
2440x1220
2500x1250

*Other formats available on request

NOMINAL THICKNESS WITH STANDARD DEVIATION, NUMBER OF PLIES, DENSITY AS PER EN 315, EN 323 & EN 324 - HARDWOOD

Nominal thickness (mm)*	Number of plies (pcs)	Standard deviation (mm)		Weight (kg/m2)	Density average (kg/m3)
6,5	5	-0,2	+0,2	4,5	640-760**
9	7	-0,2	+0,2	6,3	
12	9	-0,2	+0,2	8,4	
15	11	-0,2	+0,2	10,5	

*Other thicknesses and panel construction available on request

**As measured at 5-9% moisture content

NOMINAL THICKNESS WITH STANDARD DEVIATION, NUMBER OF PLIES, DENSITY AS PER EN 315, EN 323 & EN 324 - SOFTWOOD

Nominal thickness (mm)*	Number of plies (pcs)	Standard deviation (mm)		Weight (kg/m2)	Density average (kg/m3)
6,5	3	-0,2	+0,2	3,8	585**
9	4	-0,2	+0,2	5,3	
12	5	-0,2	+0,2	7,0	
15	7	-0,2	+0,2	8,8	

*Other thicknesses available upon request**

**As measured at 5-9% moisture content

DIMENSIONAL DEVIATION AS PER EN 315 & EN324

Length / Width	Deviation*
< 1000 mm	± 1 mm
1000 – 2000 mm	± 2 mm
> 2000 mm	± 3 mm

*Other available upon request

STRAIGHTNESS AND SQUARENESS DEVIATION AS PER EN 315 & EN 324

	Deviation
Straightness	± 0,1% or ± 1mm/m
Squareness	± 0,1% or ± 1mm/m

WARPING AS PER IN-HOUSE TECHNICAL STANDARDS

Thickness	Deviation
< 10 mm	Allowed without limitations
≥ 12 mm	Up to 10 mm/m across

RELEASE OF FORMALDEHYDE (EN717-1)

½ E1

BONDING QUALITY (EN 314-2)

Class 3

MACHINING

Edge machining and CNC machining on request

ADDITIONAL INFORMATION

1. General Terms of Sales available from www.sklejkapaged.pl
2. Declaration of Performance (DoP) available from www.sklejkapaged.pl
3. Face veneer qualities according to EN 635-3 (softwood) and EN 635-2 (hardwood).
4. CARB Phase 2 and EPA TSCA VI compliant.



Our product is made of renewable resource. Our products are characterized by low carbon footprint and are produced from certified wood, thus respecting the natural environment and the local community. The information contained in this document is intended as a guideline only and comes without warranty. We reserve the right to amend product specification sheets without notice.