

Paged Nature

Decorative hardwood plywood, moisture-resistant, finished with natural veneer

Paged Nature is a decorative plywood made from hardwood or hardwood-softwood mix. The outer layer consists of **natural veneers, with a choice of: ash, oak, walnut, pine, beech, birch, maple, alder, sapele, cherry, or anegre**. Thanks to its structure, this plywood can be used in conditions of increased humidity.

An ideal product for the furniture industry (kitchen furniture, case goods, built-in units), construction (modular building), woodware, boat building, and the transport sector (camper van outfitting).

Paged Nature plywood has been designed specifically for the decorative sector. It is therefore an excellent solution for wall cladding in offices and apartments and a prime material for use by interior designers.

The product can be manufactured with either a light or dark glue line. Both have bonding quality class 3 (EN 314-2).

> Advantages:



Attractive appearance



Bonding class



Natural veneer



Dimensional stability



Easy to machine



Sustainable development



> Standard formats** [mm]



**Non-standard sizes available on request.

> Industries and applications:




Interior & decoration



Furniture



Kitchen furniture



Wall panelling



Equipment for caravans and campers



Interior finishing



Boatbuilding



Modular construction

> Technical specifications:

| | |
|---|--|
| Fire classification*** | D-s2, d0 |
| Declaration of Performance (DoP) | Plywood for non-structural use; CE4 |
| Type of face | Natural veneer |
| Type of grain | Mixed (M), straight-grained (P), crown-cut (F) |
| Veneer species | Ash (M, F), oak (M, P, F), walnut (M), pine (M, F), beech (M), birch (M), maple (M), alder (M), sapele (M), cherry (M), anegre (M) |

*Illustrative photos. As with any natural wood product, veneers may exhibit, among others: colour variations, irregular grain patterns, natural streaks, stains, knots of various sizes, lustre, sapwood, and heartwood. These and many other differences or imperfections in veneers result from the natural origin of the raw material.

***without an air gap, for thicknesses of 9 mm and above



Declaration of Performance



Znak odpowiedzialnej gospodarki leśnej

› Thickness, number of layers, standard deviations, density [EN 315, EN 323, EN 324]

| Nominal thickness* (mm) | Number of wood layers (pcs) | Minimum deviation from nominal thickness (mm) | Maximum deviation from nominal thickness (mm) | Weight (kg/m ²) | Average density** (kg/m ³) |
|-------------------------|-----------------------------|---|---|-----------------------------|--|
| 4 | 3 | -0.4 | +0.4 | 2.8 | 640–760 |
| 5 | 4 | -0.4 | +0.4 | 3.5 | |
| 6 | 4 | -0.4 | +0.4 | 4.2 | |
| 8 | 6 | -0.4 | +0.4 | 5.6 | |
| 9 | 7 | -0.4 | +0.4 | 6.3 | |
| 10 | 7 | -0.4 | +0.4 | 6.3 | |
| 11 | 8 | -0.4 | +0.4 | 7.0 | |
| 12 | 9 | -0.4 | +0.4 | 8.4 | |
| 13 | 9 | -0.4 | +0.4 | 9.1 | |
| 15 | 11 | -0.6 | +0.6 | 10.5 | |
| 16 | 11 | -0.6 | +0.6 | 11.2 | |
| 18 | 13 | -0.6 | +0.6 | 12.6 | |
| 19 | 13 | -0.6 | +0.6 | 13.3 | |
| 21 | 15 | -0.6 | +0.6 | 14.7 | |
| 30 | 21 | -0.8 | +0.8 | 21.0 | |

* other thicknesses and custom constructions available on request

** density at 8–12% moisture content

The standard thickness of the natural veneer 0.5–0.55 mm.

› Dimensional deviations of plywood according to [EN 315, EN 324]

| Length / width | Deviation |
|----------------|-----------|
| < 1000 mm | ± 1 mm |
| 1000–2000 mm | ± 2 mm |
| > 2000 mm | ± 3 mm |

› Edge straightness and squareness deviations [EN 315, EN 324]

| | |
|----------------------------------|--------------------|
| Edge straightness and squareness | ± 0.1% or ± 1 mm/m |
|----------------------------------|--------------------|

› Standard formats*** [mm]

| |
|-------------|
| 2500 x 1250 |
|-------------|

***Non-standard sizes available on request.

› Formaldehyde emission class [EN 717-1]

E1

› Bonding quality class [EN 314-2]

CLASS 3

› Processing

- Edge machining
- CNC machining
- Drilling according to customer specifications

› Additional information

1. General Terms of Sale
2. Declaration of Performance
3. Norms and standards
4. Classification Catalogue for Surfaces of Plywood and Blockboard in Natural Veneers

Scan the QR code or click the link:
www.pagedplywood.com.

Paged

P L Y W O O D

PAGED Plywood S.A.

ul. Mazurska 1

14-300 Morąg, Poland

Helpline:

+48 87 425 48 00

pagedplywood.com



› Packaging

The plywood is stacked on pallets adapted to its dimensions. Depending on customer requirements and the method of transport, bundles are protected with cardboard and secured with strapping. The edges are protected with corner guards. The pallet height is 10–12 cm. Standard bundle heights are 60 cm and 40 cm (without pallet). The average pallet weight is 26–30 kg. Loading is carried out at the plant using forklifts. Trucks collecting the plywood must be suitable for side loading (with a minimum loading width of 2.50 m).

› Storage

Plywood sheets should be stored in a horizontal position. Do not place the sheets directly on the ground; store them on pallets that are larger than the sheets being stacked. Avoid storing plywood of different sizes, different wood species, or varying water-resistance levels in the same stack. The storage area should protect the plywood from direct exposure to water, excessive humidity, and sharp temperature changes. Plywood should be stored indoors, under controlled air parameters. Air conditioning of storage rooms is essential to balance moisture content and stresses within plywood sheets.

› Transport

During transport, plywood must be properly secured. Loading and unloading must be done in a way that prevents damage to the sheets. Vehicles transporting plywood should protect the load from water, moisture, and adverse weather conditions. Plywood bundles must be placed horizontally – stacked transport is permitted. Bundles must be secured with straps to prevent shifting during transport. Except for intermodal transport (in containers), plywood is transported using standard truck trailers that allow side unloading. The maximum load is 24 t gross (including packaging). For intermodal transport, higher values may apply.

Product Technical Data Sheet Updated on: 13/02/2026

› Pallet height



› Storage conditions



› Safety

All work must be carried out in accordance with occupational health and safety regulations.

› Supplementary documents

1. Technical Conditions
2. Plywood Storage Instructions
3. Safety Data Sheet

AVAILABLE ON REQUEST

Paged

P L Y W O O D

PAGED Plywood S.A.

ul. Mazurska 1
14-300 Morąg, Poland

Helpline:

+48 87 425 48 00

pagedplywood.com



The above data, recommendations, and guidance are based on our best knowledge, research, and experience, and have been provided in good faith, in accordance with the standards followed by our company and our suppliers. The proposed methods of application are considered common practice; however, each user of this material should ensure by all possible means (including verification of the final product under appropriate conditions) the suitability of the supplied materials for achieving their intended purpose. Neither the company nor its authorised representatives can be held liable for any losses resulting from improper or incorrect use of its materials.